

## Partial Replacement of Sand with Copper Slag in Cement Concrete: An Experimental Study

Prof. A. L. Shimpi<sup>1</sup>, Bhushan V. Bodke<sup>2</sup>, Ghanshyam C. Jadhav<sup>3</sup>,  
Aditya G. Tanpure<sup>4</sup>, Nayan N. Biraris<sup>5</sup>

<sup>1</sup>Assistant Professor, Sandip Foundation's Sandip Institute of Engineering & Management, Nashik, Maharashtra, India

<sup>2,3,4,5</sup>BE Student, Sandip Foundation's Sandip Institute of Engineering & Management, Nashik, Maharashtra, India

### ABSTRACT

Copper slag is a by-product obtained during matte smelting and refining of copper. The common management options for copper slag are recycling, recovering of metal, production of value added products such as abrasive tools, roofing granules, cutting tools, abrasive, tiles, glass, road-base construction, railroad ballast, asphalt pavements. Despite increasing rate of reusing copper slag, the huge amount of its annual production is disposed in dumps or stockpiles to date. One of the greatest potential applications for reusing copper slag is in cement and concrete production. Many researchers have investigated the use of copper slag in the production of cement, mortar and concrete as raw materials for clinker, cement replacement, coarse and fine aggregates. The use of copper slag in cement and concrete provides potential environmental as well as economic benefits for all related industries, particularly in areas where a considerable amount of copper slag is produced.

This paper studied the engineering characteristics of copper slag and its effects on the properties of cement concrete. When copper slag is used as a raw material for clinker production, it can act as both iron adjusting and mineralizing component. Further, it also improves the grind ability of the clinker. When it is used as a cement replacement or an aggregate replacement, the cement concrete containing different forms of copper slag have good performance in comparison with conventional concrete. Compressive strength of concrete at 0%

copper slag is 29.98 N/mm<sup>2</sup>, 10% copper slag is 31.67 N/mm<sup>2</sup>, 20% copper slag is 36.90 N/mm<sup>2</sup>, 30% copper slag is 39.42 N/mm<sup>2</sup>, 40% copper slag is 45.07 N/mm<sup>2</sup>, 50% copper slag is 28.80 N/mm<sup>2</sup> and for 60% copper slag is 35.65 N/mm<sup>2</sup>. Split tensile strength of concrete at 0% copper slag is 2.80 N/mm<sup>2</sup>, 10% copper slag is 3.12 N/mm<sup>2</sup>, 20% copper slag is 3.51 N/mm<sup>2</sup>, 30% copper slag is 3.87 N/mm<sup>2</sup>, 40% copper slag is 3.93 N/mm<sup>2</sup>, 50% copper slag is 3.60 N/mm<sup>2</sup> and for 60% copper slag is 3.45 N/mm<sup>2</sup>. Flexural strength of concrete at 0% copper slag is 3.99 N/mm<sup>2</sup>, 10% copper slag is 4.11 N/mm<sup>2</sup>, 20% copper slag is 4.20 N/mm<sup>2</sup>, 30% copper slag is 4.46 N/mm<sup>2</sup>, 40% copper slag is 4.57 N/mm<sup>2</sup>, 50% copper slag is 4.29 N/mm<sup>2</sup> and for 60% copper slag is 4.08 N/mm<sup>2</sup>. The study reveals that when copper slag is added in concrete partially replaced with sand, the properties of concrete are satisfactory up to 40% of copper slag. But when percentage of copper slag is increases, the compressive strength, split tensile strength and flexural strength of concrete is decreases. The effect of using copper slag in concrete by partially reducing quantities of sand reduces cost of concrete work. Compressive strength and flexural Strength is increased due to high toughness of copper slag. As the percentage of Copper slag increases the density of concrete is increased.

**KEYWORDS:** Concrete, Copper Slag, Split Tensile Strength, Flexural Strength, Compressive Strength, etc

### INTRODUCTION

Copper slag is a by-product of copper extraction by smelting. During smelting, impurities become slag which floats on the molten metal. Slag that is quenched in water produces angular granules which

are disposed of as waste or utilized as discussed below. Slag from ores that are mechanically concentrated before smelting contain mostly iron oxides and silicon oxides.

**How to cite this paper:** Prof. A. L. Shimpi | Bhushan V. Bodke | Ghanshyam C. Jadhav | Aditya G. Tanpure | Nayan N. Biraris "Partial Replacement of Sand with Copper Slag in Cement Concrete: An Experimental Study" Published in International Journal of Trend in Scientific Research and Development (ijtsrd), ISSN: 2456-6470, Volume-7 | Issue-3, June 2023, pp.528-533,

URL:  
[www.ijtsrd.com/papers/ijtsrd57426.pdf](http://www.ijtsrd.com/papers/ijtsrd57426.pdf)



IJTSRD57426

Copyright © 2023 by author (s) and International Journal of Trend in Scientific Research and Development Journal. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (CC BY 4.0) (<http://creativecommons.org/licenses/by/4.0>)



Copper slag is an abrasive blasting grit made of granulated slag from metal smelting processes (also called iron silicate). Copper slag is a by-product created during the copper smelting and refining process. As refineries draw metal out of copper ore, they produce a large volume of non-metallic dust, soot, and rock. Collectively, these materials make up slag, which can be used for a surprising number of applications in the building and industrial fields. This material represents a popular alternative to sand as a blasting medium in industrial cleaning. Using blasting or high-pressure spraying techniques, companies can use copper slag to clean large smelting furnaces or equipment. Slag blasting is also used to remove rust, paint, and other materials from the surface of metal or stone. This helps to prepare the surface for painting, or simply to remove unwanted finishes or residue. Copper slag abrasive is suitable for blast cleaning of steel and stone/concrete surfaces, removal of mill scale, rust, old paint, dirt etc.

Copper slag blasting grit is manufactured of the granulated slag of copper refineries, and used for blast-cleaning of metal surface. In different industries it is called different names - abrasive powder, grit, copper slag grit, mineral grit, grinding grains, etc. - but its main use is still for surface blast-cleaning. Blasting the grit at the surface is the most advanced approach for metal surface cleaning before paint spraying. The blasting media manufactured from copper slag brings less harm to people and environment than sand. The product meets the most rigid health and ecological standards. Copper slag can also be used as a building material, formed into blocks. Such use was common in areas where smelting was done. Due to its high strength/ weight ratio copper slag is used as filling materials in construction works. Copper slag can be used as a best alternative to sand.

Copper slag has also gained popularity in the building industry for use as a fill material. Unlike many other fill materials, copper slag poses relatively little threat to the environment. This means it can be used to build up the earth to support roads, buildings, or other surfaces. Contractors may also use copper slag in place of sand during concrete construction.



**Fig. 1: Copper Slag**

The slag serves as a fine, or binding agent, which helps hold the larger gravel particles within the concrete together. When used in this manner, the slag helps to improve the properties of the concrete, and also serves as a form of recycling. One of the primary advantages to copper slag is the low risk it poses to health and the environment. Silica sand, which represents the most popular blasting medium and concrete fine currently in use, poses serious health risks when inhaled. It may also contribute to pollution and other environmental concerns.

Copper slag also has a high strength-to-weight ratio, making it an effective option in concrete, or as a fill material under the roadway. When added to concrete, it makes the paved surface less porous, which minimizes problems with moisture and freezing. It also makes concrete more fire resistant, and helps to slow the spread of heat and flames. This material also has several limitations that users should be aware of before using copper slag. Some versions may contain heavy metal traces, which can contribute to air and water pollution.

It's commonly classified as hazardous waste due to this risk. Another issue to consider is the sheer volume of slag produced during copper refining. Typically, refineries end up with two units of slag for every one unit of copper produced during smelting.

#### **A. Physical Properties of Copper Slag**

**Table 1: Physical Properties of Copper Slag**

Sr. No.	Type	Property
1	Color	Black
2	Form	Granular
3	Purity (%)	95
4	Usage/Application	Shot blasting
5	Grade	Chemical Grade
6	Hardness (Mohr's Scale)	5 to 7
7	Specific Gravity	3.2 to 3.7
8	Type	Metallic Abrasive
9	Electric Conductivity	4.8 ms/m
10	Chloride Content	< 0.0002
11	Particle Size	0.2mm up to 3mm
12	Granular Size	Angular, sharp edges, multifaceted

**B. Chemical Properties of Copper Slag****Table 2: Chemical Properties of Copper Slag**

Sr. No.	Type	Property
1	Copper (Cu)	0.60 - 0.70
2	Ferrous Oxide (FeO)	42 - 48
3	<b>Silicon Dioxide</b> (SiO <sub>2</sub> )	26 - 30
4	Aluminium Oxide (Al <sub>2</sub> O <sub>3</sub> )	1.0 – 3.0
5	Sulfur (S)	0.2 – 0.3
6	<b>Calcium Oxide</b> (CaO)	1.0 – 2.0
7	Magnesium Oxide (MgO)	0.8 – 1.5
8	Iron Oxide (Fe <sub>3</sub> O <sub>4</sub> )	1.0 – 2.0
9	Electric Conductivity	4.8 ms/m
10	Chloride Content	< 0.0002
11	Particle Size	0.2mm up to 3mm
12	Granular Size	Angular, sharp edges, multifaceted

**METHODOLOGY****A. Problem Statement**

The use of industrial solid waste to concrete production is environmentally friendly because it contributes to reducing the consumption of natural resources, the pollution concrete production generates and the power it consumes.

**B. Aim of the Study**

The main aim of the study is to investigate the copper slag used concrete. And the achievement of an acceptable probability that concrete being designed will perform satisfactorily during their intended life. With an appropriate degree of safety, they should sustain all the loads and deformations of normal construction and use and have adequate durability and adequate resistance to the effects of heat. The realization of design objectives requires compliance with clearly defined standards for materials, production, workmanship and also maintenance and use of structure in service.

**C. Objectives of the Study**

The reported work has aimed at the development and verification of a systematic methodology for process planning and optimization for most efficient method. The objectives of this study are as follows:

1. To study the effect of copper slag on compressive strength of concrete with partial replacement of sand by 10%, 20%, 30%, 40%, 50% and 60% for 28 days of water curing for M25 grade of concrete.
2. To study the effect of copper slag on split tensile strength of concrete with partial replacement of sand by 10%, 20%, 30%, 40%, 50% and 60% for

28 days of water curing for M25 grade of concrete.

3. To study the effect of copper slag on flexural strength of concrete with partial replacement of sand by 10%, 20%, 30%, 40%, 50% and 60% for 28 days of water curing for M25 grade of concrete.
4. To compare compressive strength of concrete, split tensile strength of concrete and flexural strength of concrete with normal grade of concrete for 28 days of water curing for M25 grade of concrete. (i. e. 0% of copper slag).

**D. Methodology**

- a) Review of existing literatures by different researchers.
- b) Significance of research.
- c) Data collection.
- d) Selection of type of material and mix proportion.
- e) Testing.
- f) Data analysis & Conclusion.
- g) References


**E. Formation of Copper Slag**

Copper slag is a by-product obtained during the matte smelting and refining of copper. The major constituent of a smelting charge are sulphides and oxides of iron and copper. The charge also contains oxides such as SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, CaO and MgO, which are either present in original concentrate or added as flux. It is Iron, Copper, Sulphur, Oxygen and their oxides which largely control the chemistry and physical constitution of smelting system. A further important factor is the oxidation/reduction potential of the gases which are used to heat and melt. As a result of this process copper- rich matte (sulphides) and copper slag (oxides) are formed as two separate liquid phases. The addition of silica during smelting process forms strongly bonded silicate anions by combining with the oxides. This reaction produces copper slag phase, whereas sulphide from matte phase, due to low tendency to form the anion complexes. Silica is added directly for the most complete isolation of copper in matte which occurs at near saturation concentration with SiO<sub>2</sub>. The slag structure is stabilized with the addition of lime and alumina. The molten slag is discharged from the furnace at 1000-1300°C. When liquid is cooled slowly, it forms a dense, hard crystalline product, while a granulated amorphous slag is formed through quick solidification by pouring molten slag.

Copper slag is a by-product obtained during the mattes melting and refining of copper. Copper slag used in this work was brought from Sterlite Industries Ltd (SIL), Tuticorin, Tamil Nadu, India. SIL is



producing Copper slag during the manufacture of copper metal. Currently, about 2600 tons of Copper slag is produced per day and a total accumulation of around 1.5 million tons. It is a by-product obtained during the matte smelting and refining of copper. To produce every ton of copper, approximately 2.2–3.0 tons copper slag is generated as a by-product material. Utilization of copper slag in applications such as Portland cement substitution and/or as aggregates has threefold advantages of eliminating the costs of dumping, reducing the cost of concrete, and minimizing air pollution problems.



**Fig. 2: Preparation of Copper Slag**

## EXPERIMENTAL STUDY

### A. Test Results on Cement

**Table 5: Summary of Test Results on Cement**

Sr. No.	Description of Test	Results
1	Fineness of Cement (Residue on IS sieve No.9)	2.65 %
2	Specific Gravity	3.17
3	Standard Consistency of Cement	32 %
4	Setting Time of Cement Initial Setting Time Final Setting Time	42 min 585 min
5	Soundness Test of Cement (with Le-chatelier's mould)	9.0 mm
6	Compressive Strength of Cement (28 Days of curing)	54.22 N/mm <sup>2</sup>

### B. Test Results on Fine Aggregates

**Table 6: Summary of Test Results on Fine Aggregates**

Sr. No.	Property	Results
1	Particle Shape, Size	Round, 4.75 mm down
2	Fineness Modulus	2.683
3	Silt Content	3.3 %
4	Specific Gravity	2.94
5	Bulk Density	1723 kg/m <sup>3</sup>
6	Surface Moisture	Nil

### C. Test Results on Coarse Aggregates

**Table 7: Summary of Test Results on Coarse Aggregates**

Sr. No.	Property	Results
1	Particle Shape, Size	Angular, 10 mm down
2	Fineness Modulus	6.0
3	Specific Gravity	2.69
4	Water Absorption	2.835 %
5	Moisture content	Nil
6	Bulk Density	1620 kg/m <sup>3</sup>

### D. Mix Design of Concrete for M25 Grade

**Table 8: Mix Design of Concrete for M25 Grade**


W/C	Mixture Proportion (kg/m <sup>3</sup> )			
	Cement	Fine Aggregate	Coarse Aggregate	Water
0.45	437	654	1125	197

**Cement: Fine Aggregate : Coarse Aggregate = 1 : 1.49 : 2.57**

### E. Results of Compressive Strength Test on Concrete

**Table 9: Results of Compressive Strength Test for 28 Days of Curing with different % of Copper Slag**

Sr. No.	% of Copper Slag	Avg. Compressive Strength (N/mm <sup>2</sup> )
1	CS 0%	29.98
2	CS 10%	31.67
3	CS 20%	36.90
4	CS 30%	39.42
5	CS 40%	45.07
6	CS 50%	36.78
7	CS 60%	35.65




**Graph 1: Compressive Strength Test Results for 28 Days of Curing with different % of Copper Slag**

## F. Results of Split Tensile Strength Test on Concrete

**Table 10: Results of Split Tensile Strength Test for 28 Days of Curing with different % of Copper Slag**

Sr. No.	% of Copper Slag	Avg. Tensile Strength (N/mm <sup>2</sup> )
1	CS 0%	2.80
2	CS 10%	3.12
3	CS 20%	3.51
4	CS 30%	3.87
5	CS 40%	3.93
6	CS 50%	3.60
7	GW 60%	3.45




**Graph 2: Split Tensile Strength Test Results for 28 Days of Curing with different % of Copper Slag**

## G. Results of Flexural Strength Test on Concrete

**Table 11 Results of Flexural Strength Test for 28 Days of Curing with different % of Copper Slag**

Sr. No.	% of Copper Slag	Avg. Flexural Strength (N/mm <sup>2</sup> )
1	CS 0%	3.99
2	CS 10%	4.11
3	CS 20%	4.20
4	CS 30%	4.46
5	CS 40%	4.57
6	CS 50%	4.29
7	CS 60%	4.08



**Graph 3: Flexural Strength Test Results for 28 Days of Curing with different % of Copper Slag**

## CONCLUSION

It can be concluded that:

1. Compressive strength of concrete at 0% copper slag is 29.98 N/mm<sup>2</sup>, 10% copper slag is 31.67 N/mm<sup>2</sup>, 20% copper slag is 36.90 N/mm<sup>2</sup>, 30% copper slag is 39.42 N/mm<sup>2</sup>, 40% copper slag is 45.07 N/mm<sup>2</sup>, 50% copper slag is 28.80 N/mm<sup>2</sup> and for 60% copper slag is 35.65 N/mm<sup>2</sup>.
2. Split tensile strength of concrete at 0% copper slag is 2.80 N/mm<sup>2</sup>, 10% copper slag is 3.12 N/mm<sup>2</sup>, 20% copper slag is 3.51 N/mm<sup>2</sup>, 30% copper slag is 3.87 N/mm<sup>2</sup>, 40% copper slag is 3.93 N/mm<sup>2</sup>, 50% copper slag is 3.60 N/mm<sup>2</sup> and for 60% copper slag is 3.45 N/mm<sup>2</sup>.
3. Flexural strength of concrete at 0% copper slag is 3.99 N/mm<sup>2</sup>, 10% copper slag is 4.11 N/mm<sup>2</sup>, 20% copper slag is 4.20 N/mm<sup>2</sup>, 30% copper slag is 4.46 N/mm<sup>2</sup>, 40% copper slag is 4.57 N/mm<sup>2</sup>, 50% copper slag is 4.29 N/mm<sup>2</sup> and for 60% copper slag is 4.08 N/mm<sup>2</sup>.
4. The study reveals that when copper slag is added in concrete partially replaced with sand, the properties of concrete are satisfactory up to 40% of copper slag. But when percentage of copper slag is increases, the compressive strength, split tensile strength and flexural strength of concrete is decreases.
5. The effect of using copper slag in concrete by partially reducing quantities of sand reduces cost of concrete work.
6. Compressive strength and flexural Strength is increased due to high toughness of copper slag. As the percentage of Copper slag increases the density of concrete is increased.

## ACKNOWLEDGMENT

At the end of our project, it is a pleasant task to express our thanks to all those who contributed in many ways to the success of this study and made it an unforgettable experience for us. We would like to express our sincere gratitude to guide **Prof. A. L. Shimpi** and co-guide **Prof. P. P. Vispute**, for their excellent guidance and continuous encouragement during course of our work. We truly appreciate for their vast knowledge and delight supervision and advice. Our special thanks to **Prof. K. A. Salunke**, Head of Civil Engineering Department, for his constant inspiration and all the facilities provided to successfully complete this work. We would also like to thank **Dr. D. P. Patil**, Principal of the Institute who has provided us this opportunity to present this dissertation. We would also like to thank to all the faculty members of the department for their valuable guidance and support during the course of our work.

Also we would like to thank all our friends who have directly or indirectly helped us in our project work throughout the course. Finally we would like to thank our parents from whom we learnt the value of hard work and its fruitful results.

## REFERENCES

- [1] M. Manjunatha, T. V. Reshma, K. V. G. D. Balaji, A. Bharath, Ranjitha B. Tangadagi, "The Sustainable Use of Waste Copper Slag in Concrete: An Experimental Research", Science Direct, Materials Today Proceedings, Volume 47, Part 13, <https://doi.org/10.1016/j.matpr.2021.01.261>, 2021.
- [2] Abhishek Maharishi, S. P. Singh, Lalit Kumar Gupta and Shehnazdeep, "Strength and Durability Studies on Slag Cement Concrete Made with Copper Slag as Fine Aggregates", Science Direct, Materials Today Proceedings, Volume 38, Part 5, Pages 2639-2648, <https://doi.org/10.1016/j.matpr.2020.08.232>, 2021.
- [3] Swetapadma Panda, Pradip Sarkar and Robin Davis, "Abrasion Resistance and Slake Durability of Copper Slag Aggregate Concrete", Science Direct, Journal of Building Engineering, Volume 35, 101987, <https://doi.org/10.1016/j.jobbe.2020.101987>, March 2021.
- [4] Madhura Sridharan and T. Ch. Madhavi, "Investigating the Influence of Copper Slag on The Mechanical behaviour of Concrete", Science Direct, Materials Today Proceedings, Volume 46, Part 9, Pages 3225-3232, <https://doi.org/10.1016/j.matpr.2020.11.195>, 2021
- [5] Ruijun Wang, Qi Shi, Yang Li, Zhiliang Cao and Zheng Si, "A Critical Review on the Use of Copper Slag (CS) As A Substitute Constituent in Concrete", Science Direct, Construction and Building Materials, Volume 292, 123371, <https://doi.org/10.1016/j.conbuildmat.2021.123371>, 19 July 2021,
- [6] Nikita Gupta and Rafat Siddique, "Durability Characteristics of Self-compacting Concrete Made with Copper Slag", Science Direct, Construction and Building Materials, Volume 247, 118580, <https://doi.org/10.1016/j.conbuildmat.2020.118580>, 30 June 2020,
- [7] Poriya Dhanesh1, Raval Amit, Dr. Jayeshkumar R. Pitroda, "Sustainable Construction Material - Copper Slag: A Review", International Journal of Engineering Research, Volume No.8, Issue Special 4, Pages 10-15, 18-19 February 2019.
- [8] Prabhat Ranjan Prem, Mohit Verma and P. S. Ambily, "Sustainable Cleaner Production of Concrete with High Volume Copper Slag", Journal of Cleaner Production, Volume 193, Pages 43-58, <https://doi.org/10.1016/j.jclepro.2018.04.245>, 20 August 2018.
- [9] M. Mithun and M. C. Narasimhan, "Performance of Alkali Activated Slag Concrete Mixes Incorporating Copper Slag as Fine Aggregate", Journal of Cleaner Production, Volume 112, Part 1, Pages 837-844, <https://doi.org/10.1016/j.jclepro.2015.06.026>, 20 January 2016.
- [10] M. Baby, A. Gowshik, J. Jayaprakash, A. V. Karthick Rajeshwar, "Use of Copper Slag As A Replacement for Fine Aggregate in Concrete", International Journal of Applied Engineering Research, Volume 10, No.83, Pages 244-246, 2015.
- [11] M. V. Patil, "Properties and Effects of Copper Slag in Concrete", International Journal of Advances in Mechanical and Civil Engineering, Volume 2, Issue 2, Pages 46-50, April-2015.
- [12] Alinda Dey, Deepjyoti Dev and Purnachandra Saha, "Use of Copper Slag As Sustainable Aggregate", ICSCI 2014, ASCE India Section, Pages 317-324, October 17 – 18, 2014, Hitex, Hyderabad, Telangana, India.